



SANGEETH - YARN QUALITY

At Sangeeth, Quality is given top priority. These are the quality specifications of the standard yarns produced at SANGEETH

COUNT	10/1 O.E Weaving	40/1 Com Weaving	40/1 Com Knitting	50/1 Com Knitting	40/1 Com Compact Knitting	40/1 Com Compact Weaving
CSP	1500	2800	2400	2300	2800	3000
Count CV%	1.50	1.40	1.40	1.50	1.4	1.4
RKM (gms/tex)Tensorapid	11.00	18.50	15.50	15.00	18.00	21.00
RKM CV%	<9.0	< 8.0	< 8.0	< 8.0	< 8.00	< 8.00
U%	12.00	10.30	10.00	11.00	10.20	10.20
Thin	7	2	2	5	2	2
Thick	55	21	18	50	20	20
Neps	40	72	75	110	65	65
Total Imperfections/km	102	95	95	165	87	87
TPM	591	1024	872	984	886	1004
TPI	15.00	26.00	22.15	25.00	22.50	25.50
Elongation %	~	5.0	5.0	5.0	5.50	5.50
Elongation CV %	~	<9.0	<9.0	<9.0	< 8.0	< 8.0
Hariness	~	5.00	5.50	4.50	3.60	3.60
Total Clasimatt Faults.	~	120.00	120.00	200.00	110.00	110.00
Objectional faults/100 KM (A4+B4+C3+C4+D3+D4)	~	< 1	< 1	< 1	< 1	< 1
Long Thin/100 Km(H2+I2)	~	< 1	< 1	< 1	< 1	< 1
Long Thick/100 Km(E+F+G)	~	< 1	< 1	< 1	< 1	< 1

Note: We also make 'S' twist yarns in all above counts

E-mail: sales@sangeeth.in

Fax : +91-422-2654344